

**INSTITUTE SPECIFICATION – VERSION WITH MARKINGS TO
SHOW CHANGES MADE**

5 **Description**

~~Optical fiber cable and process for manufacture of an optical fiber cable~~

**OPTICAL FIBER CABLE AND PROCESS FOR MANUFACTURE OF AN
OPTICAL FIBER CABLE**

10

FIELD OF THE INVENTION

The present invention concerns an optical fiber cable with a cable core, which has at least one optical transmission element, and a cable jacket surrounding the cable core. Additionally, the present invention concerns a process for the manufacture of such an optical fiber cable.

15

BACKGROUND OF THE INVENTION

Optical fiber cables are manufactured in a multitude of cable constructions. When conceiving an optical fiber cable, besides other aspects, it is often the objective to construct the cable with longitudinal water impermeability, perhaps by providing filling compounds or swellable materials, which are contained in the cable core.

20

In a typical cable construction, several bundle cores are stranded around a central element, which contain one or more optical fibers. The cavities between the bundle core are filled with a filling compound. Over the stranded bundle cores, a swell tape and/or a film wrap of a plastic film is applied. Over these, tension relief elements such as yarns made of glass or aramid are applied. The cable is enclosed by a cable jacket. The longitudinal water impermeability within the cable core is guaranteed by the filling compound, in the cable jacket by swelling of swell tape during water penetration into the cable.

25

30

SUBSTITUTE SPECIFICATION – VERISION WITH MARKINGS TO SHOW CHANGES MADE

5 In a further typical cable construction, where no film wrap or swell tape is
provided around the cable core, the cavities between the bundle cores are filled
with a special pasty filling compound. This special pasty filling compound is
known as Füllnidtz filling compound ~~and~~ contains small quartz pebbles in an
emulsion. The special nature of such a filling compound makes it possible for it to
10 come in contact with the hot plastic jacket material during the extrusion process,
without the creation of blisters or jacket damage. This is necessary, since due to
eliminating the film wrap or a swell tape, respectively, around the cable core there
is no thermal protection of the filling compound during the extrusion of the cable
jacket. However, the use of such a filling compound with thermal stability leads
15 generally to an increase in the manufacturing costs for the optical fiber cable.

The use especially of swell tape has generally the disadvantage, that it shows a
relatively large thickness of f.e. 0.2 to 0.4 mm. In the described case where a
swell tape surrounds the cable core of an optical fiber cable, the cable diameter
20 has to be correspondingly large. A separate wrapping of the cable core with a
plastic film also leads to a diameter increase of the optical fiber cable. This is
especially disadvantageous, when such an optical fiber cable has to be blown into
a comparatively thin tube during the installation process. For such an installation
of an optical fiber cable, any kind of decrease in the cable diameter is of
25 advantage. A further disadvantage of the use of swell tape is the comparatively
high manufacturing cost.

ASPECTS OF THE INVENTION

It is the objective of the present invention, to create a cable construction of an
30 optical fiber cable, which enables a comparatively small cable diameter and which
can be manufactured in a comparatively cost-effective way.

**SUBSTITUTE SPECIFICATION – VERISION WITH MARKINGS TO
SHOW CHANGES MADE**

5 Additionally, it is the objective of the present invention to give a corresponding manufacturing process.

~~This objective is achieved by an optical fiber cable according to patent claim 1 and by a process for the manufacture of an optical fiber cable according to patent~~
10 ~~claim 4.~~

SUMMARY OF THE INVENTION

For the optical fiber cable according to the invention, a plastic film is provided, which surrounds the cable core and is in contact with the cable jacket. The plastic
15 film has a material, which is also contained in the cable jacket, where the plastic film is further constructed in such a way, that it becomes glued to the cable jacket during the extrusion process. In the process for the manufacture of the optical fiber cable, the plastic film is applied over the cable core before the extrusion of the cable jacket over the cable core. The cable jacket is then extruded over the
20 cable core and brought into contact with the plastic film in such a way, that it is glued to the cable jacket during its extrusion. This eliminates the use of a separate cable core wrap in the cable end product, which would increase the diameter of the cable. Since the plastic film is glued to the cable jacket during extrusion in the optical fiber cable according to the invention, the cable diameter does not increase
25 measurably, since the plastic film practically melts together with the cable jacket.

The provision of a plastic film around the cable core according to the invention fulfills a multitude of objectives, especially during the manufacture of the optical fiber cable. On the one hand, the plastic film can serve as a position fixing for the
30 filling compound present in the cable core; in addition, the plastic film prevents contamination of the stranding line and of the jacket extruder during manufacture of the optical fiber cable, while the cable core runs through several construction

**SUBSTITUTE SPECIFICATION – VERISION WITH MARKINGS TO
SHOW CHANGES MADE**

5 lines at which time the cable jacket has not been applied to the cable core. With
several optical transmission elements, f.e. in the form of stranded bundle cores,
the plastic film serves as a stabilization medium. An important advantage of the
plastic film according to the invention is found in the fact, that it serves as thermal
protection during cable manufacture, so that the heat generated during the
10 manufacturing process, in which the cable jacket is applied by extrusion, is held
away. In this way it is possible to use a comparatively cost-effective standard
filling compound.

According to this, in a further development of the invention, an optical fiber cable
15 can be created, where the cable core contains a standard filling compound, which
has a drip point below the extrusion temperature of the cable jacket. The use of a
film wrap surrounding the cable core, which is separable from the cable jacket in
the cable end product, can be eliminated.

20 ~~Further advantageous developments of the invention are given in the sub-claims.~~

~~The invention is explained in the following figures. Shown is in~~

BRIEF DESCRIPTION OF THE DRAWINTG FIGURES

25 Figure 1 is a construction form of an optical fiber cable according to the
invention,;

Figure 2 is a construction form of an optical fiber cable according to the state-of-
the-art,;

30 Figure 3 is a further construction form of an optical fiber cable according to the
state-of-the-art.

**SUBSTITUTE SPECIFICATION – VERISION WITH MARKINGS TO
SHOW CHANGES MADE**

5 DETAILED DESCRIPTION OF THE INVENTION

Figure 2 shows a typical cable construction of an optical fiber cable according to the state-of-the-art. Bundle cores 1 with optical transmission elements in the form of optical fibers 10 as well as blind elements 3 are stranded around a central element 2. The cavities thus created between the central element 2, bundle cores 1

10 and blind elements 3 are

SUBSTITUTE SPECIFICATION – VERISION WITH MARKINGS TO SHOW CHANGES MADE

- 5 filled with a standard filling compound 4. Standard filling compound means, that
the drip point of the filling compound lies below the extrusion temperature of the
cable jacket. Standard filling compounds are petrolatum containing high viscosity
liquids, which prevent dampness from reaching the bundle cores. A film wrap 5 is
applied over the stranded bundle cores 1 and the blind elements 3, over which the
10 tension relief element 6, especially in the form of yarns made of glass or aramid,
are applied. The cable is enclosed by a cable jacket 7, which contains
polyethylene in the given construction sample. The film wrap 5 can be a swell
tape or a film made of plastic in the given construction sample.
- 15 Figure 3 shows another construction form of an optical fiber cable according to
the state-of-the-art. Here the cavities within the cable core between the central
element 2, the bundle cores 1 and the blind elements 3 are filled with a special
pasty filling compound 8. This special pasty filling compound is also known as
Füllnidtz filling compound and contains small quartz pellets within an emulsion.
- 20 Into this pasty filling compound 8 the tension relief elements 6 can be inserted
and afterwards the cable jacket 7 can be extruded over it. The special nature of the
pasty filling compound 8 makes it possible, that it comes in direct contact with the
hot cable jacket material during the extrusion process without causing blisters or
jacket damage. In this way, a film wrap 5 according to Figure 2 can be eliminated.
- 25 Figure 1 shows the construction form of an optical fiber cable according to the
invention. According to Figure 1, 2 bundle cores 1 with optical fibers 10 and blind
elements 3 are stranded around a central element 2. The cavities in the interior of
the cable core 9 between the central element, bundle cores and blind elements are
30 filled with standard filling compound 4, which has a drip point below the
extrusion temperature of the cable jacket 7. Over the stranded bundle cores 1 and

**SUBSTITUTE SPECIFICATION – VERISION WITH MARKINGS TO
SHOW CHANGES MADE**

- 5 the blind elements 3, tension relief elements 6, especially yarns made of glass or
aramid, are located. The cable core 9 is surrounded by a plastic film 11, which is
in contact with the cable jacket 7. The cable jacket 7 as well as the plastic film 11
show a similar base material, especially polyethylene, polypropylene or polyvinyl
chloride. The plastic film 11 is applied over the cable core 9 before extrusion of
10 the cable jacket 7, where the plastic film 11 comes in contact with the hot cable
jacket material during the extrusion process. The plastic film 11 begins to glue to
the cable jacket 7 and normally cannot be differentiated from the cable jacket 7
after manufacture of the optical fiber cable.
- 15 The plastic film 11 serves as thermal protection, by holding away the heat being
generated from the construction elements of the optical fiber cable beneath it.
This prevents, that blind elements 3 are fused, which can lead to problems during
cable installation. It also avoids the filling compound becoming overheated and
forming blisters, which can lead to bursting of the cable jacket during
20 manufacturing. In comparison to the optical fiber cable in Figure 2, a film wrap
surrounding the cable core, which can be separated in the end product, can be
eliminated. This makes it possible, to produce the optical fiber cable according to
the invention with a comparatively smaller diameter. Against the optical fiber
cable according to Figure 3, the optical fiber cable according to the invention has
25 the advantage, that an expensive, temperature stable filling compound for the
cable core can be eliminated and instead a more cost-effective standard filling
compound can be used. Another advantage lies in the fact, that gluing together of
cable jacket and blind elements is avoided.

**SUBSTITUTE SPECIFICATION – VERISION WITH MARKINGS TO
SHOW CHANGES MADE**

- 5 The invention thus provides a cable construction for an optical fiber cable with longitudinal water impermeability, which can be produced in a comparatively cost-effective way with standard filling compounds. At the same time, a cable core wrap, which is separate from the cable jacket in the end product, can be eliminated, which is an advantage for cable construction, where such a separate
- 10 cable wrap is not desired.